

SOGAS: RESISTENCIA EN KILOGRAMOS				
MEDIDA	POLIPROPILENO	NYLON	POLIESTER ALTA TENASIDAD	PILESTER TIPO ALGODÓN
3,-	74	111	133	88
4,-	95	142	170	114
5,-	138	207	248	165
6,-	165	247	296	198
7,-	212	318	381	254
8,-	246	369	442	295
10,-	360	540	648	432
12,-	474	711	853	568
14,-	565	847	1016	678
16,-	660	990	1188	792
18,-	762	1143	1371	914
20,-	875	1312	1574	1050